



EN 14909
Dampf-proof course 0,35 mm PE
Datasheet

Characteristic	Test method	Units	Expression of result	Value of statement
Water tightness	EN 1928	kPa	-	2 kPa
Colour	-	-	-	Black
Durability (artificial ageing)	EN 1296 and EN 1928	-	Pass	Pass
Joint strenght	EN 19317-2	N/50 mm	MLV	197
Water vapour transmission properties	EN 1931	(m ² x h x kPa)/g	MDV	1600
Durability (alkali)	Annex C and EN 12113-2	-	Pass	Pass
Reaction to fire	EN 13501-1:2002	-	EN 13501-1:2002	F
Tensile strenght	-	MPa		≥ 16,1 MD ≤ 16,0 CMD
Resistance to load	-	kg		20
Resisctance to bending in low temperature	-	°C		-27
Length	EN 1848-2	m	MDV	25 ± 1%
Width	EN 1848-2	m	MDV	From 0,10 to 1,20 ± 1%
Thickness	EN 1849-2	mm	MDV	0,35
Straightness	EN 1848-2	-	Pass	Pass
Visible defect	EN 1850-2	-	Pass	No visible defects